

## DINITROL 33

Universal Protection

### Characteristics:

- Brown
- Lubricating properties
- High solids
- For moving parts

### Applications:

DINITROL 33 has a considerably wide range of application areas. It is eminently suitable for protection during storage and transportation, in the short term as well as over long periods of time. This applies to both treated and untreated steel surfaces, to finished assemblies of different types, such as engines, spare parts and motor details. DINITROL 33 has applicability in practically every situation when anti-corrosion protection is required.

### Method of use:

DINITROL 33 can be applied by dipping, brushing or by using manual and semiautomatic application equipment to a clean dry substrate and is suitable for airless spraying. The most suitable temperature for application is between 15 and 20°C.

### Technical properties:

Colour:	brown
Type of film:	greasy
Density at 23°C:	880 kg/m <sup>3</sup>
Viscosity at 23°C (DIN 2):	100 s
Dry matter content:	70% by weight
Flash point:	40°C
Recommended film thickness wet:	65 µm
Recommended layer thickness:	40 µm
Drying time:	3 hrs
Effect on car paint:	none
Low temperature adhesion:	- 40°C
Hear resistance:	90°C
Available in:	20 L Pail

For all relevant safety advices please read the material safety data sheet or the packaging label.

Die in diesem Merkblatt gemachten Angaben sind das Ergebnis sorgfältiger Untersuchungen. Soweit sie sich auf die Anwendung beziehen, sind sie als Empfehlung zu betrachten, die dem Erfahrungsstand entsprechen. Wegen der Vielseitigkeit der Anwendungs- und Arbeitsweisen können wir jedoch eine Verbindlichkeit nicht übernehmen. Es wird daher ein vertragliches Rechtsverhältnis nicht begründet, und es entstehen aus eventuellen Kaufverträgen keine Nebenverpflichtungen.

All data and recommendations are the result of careful tests by our laboratories. They only can be considered as recommendation which correspond to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the use of our products.

DINOL GmbH  
Pyrmonter Str. 76  
D-32676 Lügde  
Telefon:  
+49 (0) 52 81 / 9 82 98-0  
Telefax:  
+49 (0) 52 81 / 9 82 98-60  
E-Mail:  
service@dinol.com