

## DINITROL 8020

### Synthetic Lacquer Spray

Body Repair

Body Repair

#### Characteristics:

DINITROL 8020 Synthetic Styling Lacquer is a quick-drying acrylic lacquer. The solvent content has been carefully adapted to ensure its compatibility with all synthetic materials used for vehicle exteriors. The semi-gloss film is resistant to road salt and car washes.

#### Application:

DINITROL 8020 Synthetic Styling Lacquer is suitable for renewing plastic parts on cars and goods vehicles, sport equipment, for hobbies and in the household.

#### Method of Use:

The plastic parts to be treated must be clean, dry and free from oil and grease. Separating agents such as wax and silicone oil must be removed. In order to conserve the surface structure of plastic parts, structured surfaces should not be filed. After surface pre-treatment (i.e. removing parts which do not require treatment), spray the lacquer in an even coat at a distance of 20 – 30 cm. Depending on the absorptive capacity of the substrate, a second spraying process can be applied once dry.

#### Technical data:

Base:	Acrylic resin
Colours:	black / dark grey
Density:	0.798 g/ml
Flash point:	< -20°C
Drying time: Touch dry at 20°C	approx. 20 mins / 50 µ
Heat resistance:	> 80°C
Propellant:	Propane/butane
Removability:	Synthetic resin thinner
Storage:	cool and dry
Storage time:	24 months
Delivery form:	400 ml spray can (standard)
Hazard indication:	highly flammable

Please refer to the safety data sheet or packaging label for safety instructions.

Die in diesem Merkblatt gemachten Angaben sind das Ergebnis sorgfältiger Untersuchungen. Soweit sie sich auf die Anwendung beziehen, sind sie als Empfehlung zu betrachten, die dem Erfahrungsstand entsprechen. Wegen der Vielseitigkeit der Anwendungs- und Arbeitsweisen können wir jedoch eine Verbindlichkeit nicht übernehmen. Es wird daher ein vertragliches Rechtsverhältnis nicht begründet, und es entstehen aus eventuellen Kaufverträgen keine Nebenverpflichtungen.

All data and recommendations are the result of careful tests by our laboratories. They only can be considered as recommendation which correspond to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the use of our products.

DINOL GmbH  
Pyrmonter Str. 76  
D-32676 Lügde  
Telephone:  
+49 (0) 52 81 / 9 82 98-0  
Fax:  
+49 (0) 52 81 / 9 82 98-60  
Email:  
service@dinol.com