

# DINITROL 820

## Plastic Structure Fix Spray Black

Body Repair

Body Repair

### Characteristics:

DINITROL 820 Structure Fix Black serves to renew repaired or damaged plastic surface structures on vehicle bumpers, plastic skirting, spoilers, etc. Depending on spray distance, a finer or coarser structure can be achieved. Structure Fix adheres well to practically all plastics used in vehicle construction.

### Method of Use:

The surface to be treated must be clean and free from oil and grease.  
Shake the can well before use (1 – 2 minutes), until the mixing ball can clearly be heard.

Spray product in a cross coat at a distance of 20 – 30 cm. For small surfaces, the product can also be sprayed in a circular movement.  
In order to prevent any blockages, hold the can downwards after use and briefly spray pure gas. Depending on temperature, humidity and coat thickness, the spray is touch-dry in 30 minutes.

### Technical data:

Base:	Alkyd resin - synthetic
Colour:	black
Density:	0,813 g/ml
Flash point:	< -20
Drying time: Touch dry at 20°C:	approx. 30 mins / 50 µ
Heat resistance:	> 80°C
Propellant:	Propane/butane
Storage:	cool and dry
Storage time	24 months
Delivery form:	400 ml spray can (standard)
Hazard indication:	highly flammable

Please refer to the safety data sheet or packaging label for safety instructions.

Die in diesem Merkblatt gemachten Angaben sind das Ergebnis sorgfältiger Untersuchungen. Soweit sie sich auf die Anwendung beziehen, sind sie als Empfehlung zu betrachten, die dem Erfahrungsstand entsprechen. Wegen der Vielseitigkeit der Anwendungs- und Arbeitsweisen können wir jedoch eine Verbindlichkeit nicht übernehmen. Es wird daher ein vertragliches Rechtsverhältnis nicht begründet, und es entstehen aus eventuellen Kaufverträgen keine Nebenverpflichtungen.

All data and recommendations are the result of careful tests by our laboratories. They only can be considered as recommendation which correspond to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the use of our products.

DINOL GmbH  
Pyrmonter Str. 76  
D-32676 Lügde  
Telephone:  
+49 (0) 52 81 / 9 82 98-0  
Fax:  
+49 (0) 52 81 / 9 82 98-60  
Email:  
service@dinol.com