

DINITROL 8520

Lacquer Spray black, semi-gloss

Body Repair

Body Repair

Characteristics:

DINITROL 8520 Lacquer Spray black, semi-gloss is a quick-drying 1-c acrylic lacquer with high opacity.

Areas of Application:

Vehicle sector, industry, household. Partial lacquering of metallic surfaces such as iron and non-ferrous metals, plastics, ceramics, wood, etc. New paintwork on goods vehicle steel rims.

Method of Use:

The substrate must be clean and free from grease, dust and rust. Old and cracked paints must be removed. Lacquer and paint residue in good condition must be matt burnished. In the case of absorptive substrates, such as wood, a pore filler must be applied beforehand in order to prevent lacquer binding agent from spreading to the substrate. A fine spray lacquer pre-coat can also be applied to seal absorptive surfaces.

Before use, shake the can (1 – 2 mins) until the mixing ball can clearly be heard.

Apply the material in an even cross coat. For small surfaces, the product can also be sprayed in a circular movement. The product should be sprayed at a distance of 20 – 30 cm.

In order to prevent any blockages, hold the can downwards after use and briefly spray pure gas. Depending on temperature, humidity and coat thickness, the product is touch-dry after approx. 20 – 30 minutes.

Technical data:

Base:	Acrylic resin
Colour:	black
Density:	0.78 g/cm ³
Flash point:	< - 10
Propellant:	Propane/butane
Drying time:	approx. 20 min / 50 µm
Storage time:	24 months (cool and dry)
Recommended working temperature:	17 – 25°C
Cleaning	NC thinner or acrylic thinner
Package size:	400 ml

Note: Opened packages must be used as quickly as possible.

Please refer to the safety data sheet or packaging label for safety instructions.

Die in diesem Merkblatt gemachten Angaben sind das Ergebnis sorgfältiger Untersuchungen. Soweit sie sich auf die Anwendung beziehen, sind sie als Empfehlung zu betrachten, die dem Erfahrungsstand entsprechen. Wegen der Vielseitigkeit der Anwendungs- und Arbeitsweisen können wir jedoch eine Verbindlichkeit nicht übernehmen. Es wird daher ein vertragliches Rechtsverhältnis nicht begründet, und es entstehen aus eventuellen Kaufverträgen keine Nebenverpflichtungen.

All data and recommendations are the result of careful tests by our laboratories. They only can be considered as recommendation which correspond to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the use of our products.

DINOL GmbH
Pyrmonter Str. 76
D-32676 Lügde
Telephone:
+49 (0) 52 81 / 9 82 98-0
Fax:
+49 (0) 52 81 / 9 82 98-60
Email:
service@dinol.com