

DINITROL 8540

Lacquer Spray, white

Body Repair

Body Repair

Characteristics:

DINITROL 8540 Lacquer Spray white is a quick-drying acrylic lacquer with high opacity and good resistance. The material is extremely weather-resistant.

Application:

Vehicle sector, industry, household, partial lacquering of metallic surfaces such as iron and non-ferrous metals, plastics, ceramics, wood, etc. New paintwork on motor vehicle steel rims.

Method of Use:

The substrate must be clean and free from grease, dust and rust. Old and cracked paints must be removed. Lacquer and paint residue in good condition must be matt burnished. In the case of absorptive substrates, such as wood, a pore filler must be applied beforehand in order to prevent lacquer binding agent from spreading to the substrate. A fine spray lacquer pre-coat can also be applied to seal absorptive surfaces.

The material should be applied in an even cross coat. For small surfaces, the product can also be sprayed in a circular movement. The product should be sprayed at a distance of 20 – 30 cm.

Technical data:

Base:	Acrylic resin
Colour:	white
Density:	0.798 g/ml
Flash point:	< - 19 °C
Drying time: touch dry at 20°C:	approx. 20 min / 50 µm
Heat resistance:	> 80°C
Propellant:	Propane/butane
Storage:	cool and dry
Storage time:	24 months
Delivery form:	400 ml spray can (standard)
Hazard indication:	highly flammable

Please refer to the safety data sheet or packaging label for safety instructions.

Die in diesem Merkblatt gemachten Angaben sind das Ergebnis sorgfältiger Untersuchungen. Soweit sie sich auf die Anwendung beziehen, sind sie als Empfehlung zu betrachten, die dem Erfahrungsstand entsprechen. Wegen der Vielseitigkeit der Anwendungs- und Arbeitsweisen können wir jedoch eine Verbindlichkeit nicht übernehmen. Es wird daher ein vertragliches Rechtsverhältnis nicht begründet, und es entstehen aus eventuellen Kaufverträgen keine Nebenverpflichtungen.

All data and recommendations are the result of careful tests by our laboratories. They only can be considered as recommendation which correspond to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the use of our products.

DINOL GmbH
Pyrmonter Str. 76
D-32676 Lügde
Telephone:
+49 (0) 52 81 / 9 82 98-0
Fax:
+49 (0) 52 81 / 9 82 98-60
Email:
service@dinol.com