

DINITROL 958

Underbody Protection

Characteristics:

- Black
- Water borne
- Environmentally friendly
- Hard film
- Stone chip protection
- No labelling

Applications:

DINITROL 958 is quick drying water based stone chip protection product. DINITROL 958 provides a black elastic film, which efficiently protects the vehicle body from stone chips and road salt. DINITROL 958 is environmental friendly as it is free from solvent.

DINITROL 958 is designed for treatment of cars, buses, trucks and other vehicles, on line application as well as in the aftermarket. The product is designed to protect the most exposed parts such as doorsills, spoilers, bumpers, wheel arches, and edges. DINITROL 958 can after drying be over painted with most car lacquers.

Method of use:

DINITROL 958 can either be applied with brush, low or high pressure equipment. The spraying is recommended airless with a product temperature of +15°C – +20°C.

Technical properties:

Colour:	black
Type of film:	elastic
Density:	1300 kg/m ³
Viscosity at 23°C:	7500 mPa s
Dry matter content:	63% by weight
Rec. film thickness:	200 – 300 µm
Drying time:	45 min under optimal conditions
Effect on car paint:	none
Removability:	Water and alkaline cleaner
Heat resistance:	> 100°C
Salt spray resistance at 300 µm:	> 1000 h
Shelf life:	12 month
Available in:	20 L Pail / 208 L Drum

For all relevant safety advices please read the material safety data sheet or the packaging label.

Die in diesem Merkblatt gemachten Angaben sind das Ergebnis sorgfältiger Untersuchungen. Soweit sie sich auf die Anwendung beziehen, sind sie als Empfehlung zu betrachten, die dem Erfahrungsstand entsprechen. Wegen der Vielseitigkeit der Anwendungs- und Arbeitsweisen können wir jedoch eine Verbindlichkeit nicht übernehmen. Es wird daher ein vertragliches Rechtsverhältnis nicht begründet, und es entstehen aus eventuellen Kaufverträgen keine Nebenverpflichtungen.

All data and recommendations are the result of careful tests by our laboratories. They only can be considered as recommendation which correspond to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the use of our products.

DINOL GmbH
Pyrmonter Str. 76
D-32676 Lügde
Telefon:
+49 (0) 52 81 / 9 82 98-0
Telefax:
+49 (0) 52 81 / 9 82 98-60
E-Mail:
service@dinol.com