

## DINITROL AB 429 FSO

### Characteristics:

DINITROL AB 429 FSO is a quick drying waterbased stone chip protection product. DINITROL AB 429 FSO provides a black elastic film which efficiently protects the vehicle body from stone chips and road salt. DINITROL AB 429 FSO is environmental friendly.

### Range of use:

DINITROL AB 429 FSO is designed for treatment of cars, buses, trucks and other vehicles, on line application as well as in the aftermarket. The product is designed to protect the most exposed parts such as door sills, spoilers, bumpers, wheel arches, edges. DINITROL AB 429 FSO can be over painted after drying with most car lacquers.

### Application:

DINITROL AB 429 FSO can either be applied with brush, low or high pressure equipment. The spraying is recommended airless with a product temperature of + 15°C – 20°C.

### Technical properties:

Colour:	black	
Type of film:	elastic	
Density at 20°C:	1280 kg/m <sup>3</sup>	
Viscosity, dynamic at 20°C:	6500 – 8000 mPa s	
pH value:	8,5 – 9,5	
Dry matter content:	61% by weight	
Rec. film thickness, dry:	200 – 300 µm	
Drying time:	4 – 5 h at 23°C	
Effect on car paint:	none	SS 186011
Removability:	Water and alkaline cleaner	
Heat resistance:	> 90°C	SS 186035

For all relevant safety advices please read the material safety data sheet or the packaging label.

Die in diesem Merkblatt gemachten Angaben sind das Ergebnis sorgfältiger Untersuchungen. Soweit sie sich auf die Anwendung beziehen, sind sie als Empfehlung zu betrachten, die dem Erfahrungsstand entsprechen. Wegen der Vielseitigkeit der Anwendungs- und Arbeitsweisen können wir jedoch eine Verbindlichkeit nicht übernehmen. Es wird daher ein vertragliches Rechtsverhältnis nicht begründet, und es entstehen aus eventuellen Kaufverträgen keine Nebenverpflichtungen.

All data and recommendations are the result of careful tests by our laboratories. They only can be considered as recommendation which correspond to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the use of our products.

DINOL GmbH  
Pyrmonter Str. 76  
D-32676 Lügde  
Telefon:  
+49 (0) 52 81 / 9 82 98-0  
Telefax:  
+49 (0) 52 81 / 9 82 98-60  
E-Mail:  
service@dinol.com