

DINITROL ML

Cavity Protection

Characteristics:

- Brown
- Extremely Penetrating
- Stops ongoing corrosion
- Water displacing
- Oily, flexible film
- Wet in wet with bitumen UBC

Applications:

DINITROL ML is designed for application into closed cavities such as doors, frame members and exterior joints and crevices. The product can be used for rust-proofing of second-hand cars, trucks, buses and other vehicles.

Method of use:

DINITROL ML is applied by spraying with manual or semi-automatic. DINITROL application equipment, and is suitable for either air-mixed or airless spraying.

Technical properties:

Colour:	brown
Type of film:	oily, greasy
Density at 23°C:	860 kg/m ³
Viscosity at 23°C, DIN 2:	60 s
Dry matter content:	46 % by weight
Flash point:	40°C
Aromatic content in solvent:	< 1 %
Rec film thickness:	10 µm
Drying time:	1 h
Low temperature adhesion:	< - 40°C
Effect on car paint:	none
Removability:	White Spirit
Salt spray test:	> 96 h
Penetration 50 µm gap:	> 70 mm

Available in:	500 ML Spray can / 1 L Mini service / 5 L Pail / 20 L Pail / 60 L Drum / 208 L Drum / Container
---------------	---

For all relevant safety advices please read the material safety data sheet or the packaging label.

Die in diesem Merkblatt gemachten Angaben sind das Ergebnis sorgfältiger Untersuchungen. Soweit sie sich auf die Anwendung beziehen, sind sie als Empfehlung zu betrachten, die dem Erfahrungsstand entsprechen. Wegen der Vielseitigkeit der Anwendungs- und Arbeitsweisen können wir jedoch eine Verbindlichkeit nicht übernehmen. Es wird daher ein vertragliches Rechtsverhältnis nicht begründet, und es entstehen aus eventuellen Kaufverträgen keine Nebenverpflichtungen.

All data and recommendations are the result of careful tests by our laboratories. They only can be considered as recommendation which correspond to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the use of our products.

DINOL GmbH
Pyrmonter Str. 76
D-32676 Lügde
Telefon:
+49 (0) 52 81 / 9 82 98-0
Telefax:
+49 (0) 52 81 / 9 82 98-60
E-Mail:
service@dinol.com