

DINITROL PASTA

Universal Protection

Characteristics:

- Red
- Waxy film
- Lubrication
- High solids

Applications:

DINITROL PASTA is coloured, hence it is easy for the user to ensure that the coating of grease is even and covers the entire surface.

DINITROL PASTA is primarily intended for protection of machines, machinery components, spare parts and other iron and steel objects to be stored or transported under corrosion inductive conditions. DINITROL PASTA gives excellent protection both on treated and untreated surfaces and is particularly suited on details like moving parts, which are difficult to clean, as DINITROL PASTA is oil soluble.

Method of use:

DINITROL PASTA is applied by brushing. The paste should be applied evenly, particularly when the object is to be stored in the open air.

Technical properties:

Colour:	red
Type of film:	greasy
Density at 23°C:	860 kg/m ³
Flash point:	55°C
Min storage temperature:	- 20°C
Rec film thickness:	50 – 75 µm (dry film)
Drying time:	2 – 5 h
Consumption:	0,06 kg/m ²
Salt spray test at 100 µm Dry film:	> 240 h
Humidity test at 100 µm Dry film:	> 1000 h
Available in:	10 L Pail / 25 L Pail

For all relevant safety advices please read the material safety data sheet or the packaging label.

Die in diesem Merkblatt gemachten Angaben sind das Ergebnis sorgfältiger Untersuchungen. Soweit sie sich auf die Anwendung beziehen, sind sie als Empfehlung zu betrachten, die dem Erfahrungsstand entsprechen. Wegen der Vielseitigkeit der Anwendungs- und Arbeitsweisen können wir jedoch eine Verbindlichkeit nicht übernehmen. Es wird daher ein vertragliches Rechtsverhältnis nicht begründet, und es entstehen aus eventuellen Kaufverträgen keine Nebenverpflichtungen.

All data and recommendations are the result of careful tests by our laboratories. They only can be considered as recommendation which correspond to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the use of our products.

DINOL GmbH
Pyrmonter Str. 76
D-32676 Lügde
Telefon:
+49 (0) 52 81 / 9 82 98-0
Telefax:
+49 (0) 52 81 / 9 82 98-60
E-Mail:
service@dinol.com