

DINITROL 28

Universal Protection

Characteristics:

- Thin wax-based corrosion preventative.
- Forming a hard, tack-free film.
- Composition suitable for food-contact applications

Applications:

Suitable for various applications e.g protection during storage of components. Can be used for permanent protection of areas that are not exposed to severe corrosive conditions. The product is used for applications in the food industry.

Method of use:

DINITROL 28 may be applied by dipping, brushing or spraying. The best result will be obtained by spraying procedure. Spraying may be done by using either air less or air mix type of equipment.

Solvent such as aliphatic hydrocarbon can easily remove the film. For the assembly or control of the parts treated with DINITROL 28, it is not necessary to remove the film.

Technical properties:

Colour:	transparent
Type of film:	tack free
Density at 23°C:	790 kg/m ³
Dry matter content:	12% by weight
Flash point:	12°C
Recommended layer thickness:	1 – 10 µm
Recommended film thickness wet:	100 µm
Drying time:	1 – 10 min µm
Removability:	Alkaline
Available in:	20 L Pails

For all relevant safety advices please read the material safety data sheet or the packaging label.

Die in diesem Merkblatt gemachten Angaben sind das Ergebnis sorgfältiger Untersuchungen. Soweit sie sich auf die Anwendung beziehen, sind sie als Empfehlung zu betrachten, die dem Erfahrungsstand entsprechen. Wegen der Vielseitigkeit der Anwendungs- und Arbeitsweisen können wir jedoch eine Verbindlichkeit nicht übernehmen. Es wird daher ein vertragliches Rechtsverhältnis nicht begründet, und es entstehen aus eventuellen Kaufverträgen keine Nebenverpflichtungen.

All data and recommendations are the result of careful tests by our laboratories. They only can be considered as recommendation which correspond to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the use of our products.

DINOL GmbH
Pyrmonter Str. 76
D-32676 Lügde
Telefon:
+49 (0) 52 81 / 9 82 98-0
Telefax:
+49 (0) 52 81 / 9 82 98-60
E-Mail:
service@dinol.com