

DINITROL Rustoff

Release Agent

Characteristics:

- Lubricating
- Release agent
- Extremely penetrating
- Rust removing

Applications:

DINITROL RUSTOFF is an isoparaffinic solvent based penetrating rust-removal and release agent, permeating thick rust layers and creeping into every crevice and corner. DINITROL RUSTOFF can be used on moist surfaces and will also dissolve tar, pitch, protective undercoating compound etc., leaving a thin rust preventive oil film, containing lubricants and colloidal graphite. DINITROL RUSTOFF is an efficient agent for quick release of rusted items exhibiting a high level of efficacy & penetration.

Method of use:

The product is sprayed or brushed onto the item to be released. In general DINITROL RUSTOFF acts within 5 – 30 minutes. When cleaning or dismantling larger items such as driving chains, motors and the like, the items can be immersed in DINITROL RUSTOFF for 5 – 30 minutes, after which they can easily be dismantled and cleaned.

Technical properties:

Density at 23°C:	790 kg/m ³
Viscosity at 23°C:	2.2 mPas
Flash point active content:	41°C
Flash point Spray material:	< 0°C
Recommended film thickness wet:	100 µm
Surface tension at 20°C:	32 dyn/cm ²
Available in:	500 ml Spray can

For all relevant safety advices please read the material safety data sheet or the packaging label.

Die in diesem Merkblatt gemachten Angaben sind das Ergebnis sorgfältiger Untersuchungen. Soweit sie sich auf die Anwendung beziehen, sind sie als Empfehlung zu betrachten, die dem Erfahrungsstand entsprechen. Wegen der Vielseitigkeit der Anwendungs- und Arbeitsweisen können wir jedoch eine Verbindlichkeit nicht übernehmen. Es wird daher ein vertragliches Rechtsverhältnis nicht begründet, und es entstehen aus eventuellen Kaufverträgen keine Nebenverpflichtungen.

All data and recommendations are the result of careful tests by our laboratories. They only can be considered as recommendation which correspond to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the use of our products.

DINOL GmbH
Pyrmonter Str. 76
D-32676 Lügde
Telefon:
+49 (0) 52 81 / 9 82 98-0
Telefax:
+49 (0) 52 81 / 9 82 98-60
E-Mail:
service@dinol.com