

DINITROL 460

Characteristics:

DINITROL 460 is a permanently elastic, UV-resistant sealing compound with a high solid matter content for vehicle repair. Ideal for sealing non-bonded vehicle windows. DINITROL 460 can also be used as a sealant between rubber profiles and bodywork joints, in addition to sealing glass sunroofs. Once dry, the sealer is permanently elastic and does not become brittle. It is not harmful to chromium, paints and rubber parts.

Method of Use:

The surface to be treated must be free from oil, dust and grease.
Position the tip of the nozzle between the glass and the rubber seal or between metal and rubber profile and spray the sealer with a suitable cartridge gun.
Excess sealer can be removed with a plastic spatula and wiped with a cloth soaked in petroleum spirit, or dabbed with a lint-free cloth.

Technical properties:

Base:	rubber / synthetic resin
Colour:	black
Density:	1.45 g/cm ³
Flash point:	- 8°C
Solids content:	71%
Temperature resistance:	- 20 to +80°C
Package size:	310 ml plastic cartridge
Storage time:	between 15°C and 25°C 24 months
Hazard indication:	highly flammable

Health and safety information can be obtained from the material safety data sheet and the product label.

Die in diesem Merkblatt gemachten Angaben sind das Ergebnis sorgfältiger Untersuchungen. Soweit sie sich auf die Anwendung beziehen, sind sie als Empfehlung zu betrachten, die dem Erfahrungsstand entsprechen. Wegen der Vielseitigkeit der Anwendungs- und Arbeitsweisen können wir jedoch eine Verbindlichkeit nicht übernehmen. Es wird daher ein vertragliches Rechtsverhältnis nicht begründet, und es entstehen aus eventuellen Kaufverträgen keine Nebenverpflichtungen.

All data and recommendations are the result of careful tests by our laboratories. They only can be considered as recommendation which correspond to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the use of our products.

DINOL GmbH
Pyrmonter Str. 76
D-32676 Lügde
Telefon:
+49 (0) 52 81 / 9 82 98-0
Telefax:
+49 (0) 52 81 / 9 82 98-60
E-Mail:
service@dinol.com